

LIGHT TRANSMISSION OF DPS® TRANSLUCENT MATERIALS

1. Light transmission of PCV materials [%]

No	Name	Ref.	Total transmission coefficient [%]	Width [m]
1.	CRISTAL RIVER	T 5000	85,6	1,35
2.	CRISTAL	T 5001	51,4	1,95
3.	CRISTAL CLEAR	T 5002	76,8	2,0
4.	CRISTAL PEARL	T 5066	50,7	2,0
5.	CRISTAL WHITE	T 5077	48,6	2,0
6.	CRISTAL MOON	T 5240	54,0	2,4
7.	CRISTAL LARGE	T 5325	63-64	3,25
8.	CRISTAL XLARGE	T 5500	60-61	5,0

2. Light transmission of textile materials [%]

No	Name	Ref.	Total transmission coefficient [%]	Width [m]
1.	LIGHT WHITE	TR 042	26,9	4,9
2.	LIGHT MOON	TR 083	31,9	4,9
3.	LIGHT CREAM	TR 137	26,9	4,9
4.	LIGHT VISION	TR 173	35,7	4,9
5.	LIGHT SILK	TR 140	14,5	4,9
6.	LIGHT SOFT	TR 123	26,9	3,0