

LIGHT TRANSMISSION OF DPS® TRANSLUCENT MATERIALS

1. Light transmission of PCV materials [%]

No	Name	Ref.	Total transmission coefficient [%]
1.	CRISTAL RIVER	T 5000	85,6
2.	CRISTAL	T 5001	51,4
3.	CRISTAL CLEAR	T 5002	78
4.	CRISTAL FROST	T 5003	94
5.	CRISTAL PEARL	T 5066	50,7
6.	CRISTAL WHITE	T 5077	48,6
7.	CRISTAL MOON	T 5240	54
8.	CRISTAL XLARGE	T 5500	50

2. Light transmission of textile materials [%]

No	Name	Ref.	Total transmission coefficient [%]
1.	LIGHT VISION	TR 173	35,7

Textile materials with different light transmittance – on request